

Fire Bricks : High Alumina: Low Iron

Product	A.P (%)	B.D (gm/cm ³)	C.C.S (kg/cm ²)	RUL Ta (°C)	PLC at °C/hrs. (%)	Refractoriness (°C)	Al ₂ O ₃ (%)	Fe ₂ O ₃ (%)	Other (%)	Primary Raw Material
VRPL-50K	21	2.30	450	1480	1480/2 ±0.5	+1800	50	1.5		Kyanite
VRPL-SILL	21	2.35	450	1500	1500/2 ±0.5	+1800	56	1.5		Kyanite/Sillimanite
VRPL-SILL D	18	2.38	500	1520	1500/2 ±0.5	+1800	58	1.2	Alkali 0.8	Kyanite/Sillimanite
VRPL-60K	20	2.35	500	1520	1500/2 ±0.5	+1800	60	1.5		Kyanite/Sillimanite
VRPL-62	21	2.42	500	1520	1500/2 ±0.5	+1800	62	1.5		Sillimanite/Alumina
VRPL-62D	18	2.48	600	1550	1600/2 ±0.5	+1800	62	1.2	Alkali 0.8	Sillimanite/Alumina
VRPL-60TB	21	2.40	450	1540	1600/2 ±0.5	+1800	60	1.2		Sillimanite/Alumina
VRPL-62SD	16	2.55	650	1580	1600/2 ±0.3	+1800	63	1.0	Alkali 0.6	Sillimanite/Fused Alumina
VRPL-70D	18	2.65	600	1600	1600/2 ±0.3	+1800	70	1.0	Alkali 0.5	Sillimanite/Fused Alumina