

## High Alumina and Zircon Mortar, Patching & Ramming Masses

Product	Grain size (mm)	Type of setting	Sintering Temperature °C	Al <sub>2</sub> O <sub>3</sub> (%) min	ZrO <sub>2</sub> (%) min
VRPL SET-70K	0 - 0.5	Chemical	1200	69.0	
VRPL SET-90K	0 - 0.5	Chemical / Ceramic	1200	89.0	
VRPL ZSM	0 - 0.5	Chemical	1000 - 1100		50.0
VRPL ZMM	0 - 0.5	Chemical	1000 - 1100	65.0	15.0
VRPL PATCH ZS	0 - 2	Chemical	1000 - 1100		50.0
VRPL PATCH ZM	0 - 2	Chemical	1000 - 1100	55.0	24.0
VRPL RAM ZS	0 - 2	Chemical	1100 - 1150		50.0